



June 6, 2022

Capitol Cement LEED Statement

Capitol Cement is manufactured at our cement plant located in San Antonio Texas. All of the major materials used in the manufacture of our cement products are obtained locally either at the cement plant site or within 10 miles of the plant. Fly ash inter-ground into our EcoMent Endure is produced at a power plant 127 miles from our cement plant. The only material obtained outside the local area is gypsum which comprises approximately 3% of the weight of our cement. There is no source of gypsum in Texas so all cement produced in the state contains gypsum sourced outside Texas.

Capitol EcoMent® cements meet all the requirements of ASTM C595 *Specification for Blended Hydraulic Cement*. Cement. EcoMent® also contributes to LEED certification due to the post-industrial recycled material incorporated into its composition. Additional LEED consideration is available under the Regional Manufactured credit category. Capitol cement is manufactured at our cement plant located at 11551 Nacogdoches Road, San Antonio Texas.

The recycled material used in the manufacture of EcoMent® Spec(IL15) EcoMent® Endure(I-P25), Capitol Type I and Type III Cement is as follows:

Product	Material	Content (Percent by Weight)
Capitol Type I, Type III, EcoMent® Spec(IL15) Cement	Synthetic Gypsum	3-5%
EcoMent® Endure(I-P25)	Synthetic Gypsum Fly Ash	3-5% 25%

The Hunter Color value of Capitol Cement ranges from 62-65 on the L scale.

Capitol Cement also is eligible for a full LEED credit because it has an individual EPD. (available on request)

Additionally, the carbon footprint for Capitol cement is reduced by approximately 33% as CO2 is diverted to the CarbonFree capture facility and repurposed as baking soda and other by-products.



Rusty Winters
Director of Technical Services
Capitol Aggregates Inc.
rusty@capagg.com

ATTENTION: NO WARRANTY. The information and test results contained in this document are provided by Capitol Aggregates, Inc. without any warranty, guarantee, or representation of any kind whether statutory, express, implied, including without limit, any related to the samples tested, any cement products, testing facilities, qualifications of testing personnel, testing means, methods or results, or the suitability, safety or utility of, or compliance by any of the forgoing with any legal, regulatory, performance or any other safety standard, accuracy, FITNESS FOR ANY PARTICULAR PURPOSE, in any event regardless of trade use or custom of dealing. This information is provided as a courtesy only, not for hire, and is not intended to induce reliance by any person or entity.